

SPECIFICATION FOR EPDM RECLAIM RUBBER

Appearance	:	Black Rubber Slabs
Source	:	Factory Rejects of High Quality EPDM Profiles
Physical Form	:	Rubber Sheets

CHEMICAL PROPERTIES

Ash %	:	12 ± 2
Carbon Black %	:	25 ± 2
Acetone Extraction %	:	30 ± 5
RHC by Difference %	:	31 Min.

PHYSICAL PROPERTIES

Sp. Gravity Gm/CC	:	1.15 ± 0.03
Tensile Strength Kg/Cm ²	:	60 Min.
Elongation at Break %	:	375 Min.
Hardness Shore A	:	55 ± 5
Mooney Viscosity	:	25 - 45
ML (1 + 4) at 100 C		

Disclaimer: The information contained herein with regards to all products specification, is based on technical data and tests which we believe to be reliable. However, we assume no responsibility for results obtained or damage, if any, incurred through the application of data given, since conditions of use are outside our control.