

SPECIFICATION FOR NYLON WHOLE TYRE RECLAIM RUBBER

GRADE: HIGHLY REFINED (HR)

Sr.No	Properties	Standard Specification
1.	Acetone Extract %	15 ± 3
2.	Ash Content %	7 ± 3
3.	Carbon Black %	26 ± 4
4.	Moisture	1 Max
5.	Elongation at break	220 Min
6.	Hardness	59 ± 3
7.	**Mooney Viscosity ML at 100°C 1+4	25-45
8.	Specific Gravity Gm/cc	1.12 ± 0.02
9.	Tensile Strength Kg/cm ²	45 Min
10.	Rubber Hydrocarbon %	49 Min

Disclaimer: The information contained herein with regards to all products specification, is based on technical data and tests which we believe to be reliable. However, we assume no responsibility for results obtained or damage, if any, incurred through the application of data given, since conditions of use are outside our control.