Godrej Industries Limited

Regd. office: Pirojshanagar, Eastern Express Highway, Vikhroli, Mumbai 400 079. India
Tel: (91-22) 25188010 / 25188020 / 25188030 extn: 4388 Fax: (91-22) 25188096 / 25188068
e-mail:rv.dubhashi@godrejinds.com

LUBSTRIC 995
(RUBBER GRADE STEARIC ACID)

SPECIFICATIONS:

Rev. No. 01, dtd. 01/08/2015

CARBON CHAIN DISTRIBUTION BY GC (%)

VARIABLE

PARAMETERS		SPECIFICATIONS
Appearance	:	Light cream to brown flakes
Odour	:	Characteristic
Colour 1" Lovibond Cell – Red	:	10.0 Max
Colour 1" Lovibond Cell – Yellow	:	50.0 Max
Titre ^{O}C	:	50.0 - 60.0
Acid Value, mgm KOH/gm.	:	195.00 - 210.00
Iodine Value, g I_2/100gms	:	9.0 Max
Saponification Value, mgm KOH/gm.	:	196.00 - 215.00
% Moisture	:	0.5 Max
% Ash	:	0.1 Max

Reason for Revision: Acid Value & Saponification Value revised. Change in manufacturing site (Vikhroli to Ambernath)

- Manufactured at Ambernath & Valia
- Packing :
  - 25 Kg HDPE Laminated bags
- Broad Uses:
  - Rubber & Tyres
- Kosher Certified